



C1S Litho

Physical Test		Test Method	* Basis Weight * (based on 25x38)		
Kind of Test		Reference	60 lb	70 lb	80 lb
Grammage	g/m ²	T410 om-98	89 ± 4%	104 ± 4%	118 ± 4%
	lb		60.0 ± 4%	70.0 ± 4%	80.0 ± 4%
Thickness	µm	T411 om-97	80 ± 4	100 ± 4	116 ± 4
	Point		3.15 ± 0.16	3.93 ± 0.16	4.57 ± 0.16
Brightness		ISO 2470-1977	90	90	90
Opacity, %		ISO 2471-1977	≥ 91	≥ 93	≥ 95
Roughness	TS	ISO8791	< 0.8	< 1.0	< 1.0
	BS				
Gloss before printing, %		T480 om-92	>75	>70	>70

June 2009 Edition