



C2S Gloss Cover

		Test Method	* Basis Weight * (based on 20x26)		
		Reference	80 lb	100 lb	111 lb
Basis Weight	LB	T410 om-98	80.0 ± 4%	100.0 ± 4%	111.0 ± 4%
Thickness	Point	T411 om-97	8.2 ± 0.16	10.4 ± 0.16	12.1 ± 0.16
Smoothness, sec/10cc		(BEKK)	>250	>180	>180
Brightness, %ISO		ISO 2470-1977	89 ± 2	89 ± 2	89 ± 2
Opacity, %		ISO 2471-1977	≥99	≥99	≥99
Gloss before printing, %		T480 om-92	>70	>70	>70