



C2S Silk Cover

		Test Method	* Basis Weight * (based on 20x26)	
			Reference	80 lb
Basis Weight	LB	T410 om-98	80.0 ± 4%	100.0 ± 4%
Thickness	Point	T411 om-97	8.6 ± 0.16	11.2 ± 0.16
Smoothness, sec/10cc		(BEKK)	>180	>180
Brightness, %ISO		ISO 2470-1977	90 ± 2	90 ± 2
Opacity, %		ISO 2471-1977	≥99	≥99
Gloss before printing, %		T480 om-92	>30	>30